



Contribution ID: 314 Contribution code: O-37

Type: Oral

Muonium states in semiconducting transition metal dichalcogenides

Thursday, 1 September 2022 14:40 (20 minutes)

The usual response of muonium to an external magnetic field is dominated by the hyperfine interaction, which causes the observed spectrum to show the transition frequencies between different muonium spin states. However, we have recently discovered an unconventional magnetic muonium state in 2H-MoTe₂ where the muonium acts a magnetic impurity, which polarizes the local electronic magnetic moments [1]. For sufficiently small externally applied fields, the “magnetic” muonium effectively behaves as a diamagnetic muon in a local magnetic field. Here, we show experimentally that in 2H-MoTe₂ the magnetic muonium coexists with another conventional, non-magnetic muonium state (Fig. 1b). The latter is axially symmetric with a hyperfine coupling of $A_{\parallel}=1426(1)$ MHz and $A_{\perp}=1368(3)$ MHz, corresponding to an effective Bohr radius of ≈ 0.82 Angstrom. The hyperfine coupling remains fairly constant, as a function of temperature, until the state disappears around the same temperature where the magnetic muonium disappears as well. We employ density functional theory calculations to reveal that this is linked to the presence of two muonium sites in the compound: one within the van der Waals gap that becomes magnetic, and a second one inside the layer, that is conventional. A similar behavior is also observed in 2H-WSe₂ (Fig. 1a), indicating that this is a more general feature of semiconducting transition metal dichalcogenides.

[1] J. A. Krieger, et al., arXiv:2206.03051 (2022)




Figure 1: (a) Local field distribution in 2H-WSe₂ at 5K in a 0.7T transverse field. (b) Applied field dependence of the oscillation frequencies in 2H-MoTe₂ at 5.5K.

Primary author: KRIEGER, Jonas A. (Max Planck Institute of Microstructure Physics)

Co-authors: RUSINOV, Igor P. (Tomsk State University, pr. Lenina 36, 634050 Tomsk, Russia); Dr GUGUCHIA, Zurab (Laboratory for Muon Spin Spectroscopy, Paul Scherrer Institute, CH-5232 Villigen PSI, Switzerland); BARUA,

Sourabh (Department of Physics, University of Warwick, Coventry CV4 7AL, UK); Dr BISWAS, Pabitra (STFC / UKRI); KOROSSEC, Lukas (Laboratorium für Festkörperphysik, ETH Zürich, CH-8093 Zürich, Switzerland); Dr PROKSCHA, Thomas (PSI); Dr SCHEUERMANN, Robert (Laboratory for Muon Spin Spectroscopy, Paul Scherrer Institut, CH-5232 Villigen PSI, Switzerland); SCHMITT, Thorsten (Swiss Light Source, Paul Scherrer Institute, CH-5232 Villigen PSI, Switzerland); SCHRÖTER, Niels B. M. (Max Planck Institut für Mikrostrukturphysik, Weinberg 2, 06120 Halle, Germany); SHANG, T. (Key Laboratory of Polar Materials and Devices (MOE), School of Physics and Electronic Science, East China Normal University); Dr SHIROKA, Toni (Laboratory for Muon Spin Spectroscopy, Paul Scherrer Institute, CH-5232 Villigen PSI, Switzerland); Dr SUTER, Andreas (PSI); TAY, Daniel (Laboratorium für Festkörperphysik, ETH Zürich, CH-8093 Zürich, Switzerland); Prof. BALAKRISHNAN, Geetha (Warwick University); Dr CHULKOV, Evgueni V. (DIPC, Donostia, Spain); PARKIN, Stuart S. P. (Max Planck Institut für Mikrostrukturphysik, Weinberg 2, 06120 Halle, Germany); STROCOV, Vladimir N. (Swiss Light Source, Paul Scherrer Institute, CH-5232 Villigen PSI, Switzerland); SALMAN, Zaher (Paul Scherrer Institute)

Presenter: KRIEGER, Jonas A. (Max Planck Institute of Microstructure Physics)

Session Classification: Oral contributions

Track Classification: Semiconductors